



STYRON 695

General Purpose Polystyrene Resin

STYRON™ 695 is a high heat resistance, high tensile strength, high stiffness, and reduced residuals general purpose polystyrene resin. It is recommended in applications where minimal taste and odor, strength and heat resistance properties are important. It is recommended for use in oriented polystyrene sheet.

- Main Characteristics
- High Heat Resistance
  - Reduced Residuals
  - High Strength
  - FDA Compliant <sup>(1)</sup>

- Applications
- Oriented Sheet (OPS)
  - Foam sheet
  - Packaging/Disposables
  - Extrusion

Properties <sup>(2)</sup>	Test Method		S.I.		English		Metric		
	ISO	ASTM	Value	Unit	Value	Unit	Value	Unit	
<b>Physical</b>									
Melt flow rate (200°C / 5 kg)	1133	D 1238	1.5	g/10 min	1.5	g/10 min	1.5	g/10 min	
Specific Gravity	1183	D 792	1.04		1.04		1.04		
Linear Thermal Expansion (10 <sup>-5</sup> )	1135	D 696	9.0	cm/cm /°C	5.0	in/in/°F	9.0	cm/cm/°C	
Mold Shrinkage		D 955	0.003 - 0.007	cm/cm	0.003 - 0.007	in/in	0.003 - 0.007	cm/cm	
<b>Optical</b>									
Transmittance		D 1003	90	%	90	%	90	%	
Haze		D 1003	1.0	%	1.0	%	1.0	%	
Refractive Index		D 542	1.59		1.59		1.59		
<b>Thermal</b>									
Vicat Softening Temperature (120°C/hr, 1 kg)	306A	D 1525-B	108	°C	227	°F	108	°C	
Deflection Temperature Under Load (Injection molded)	75A	D 648							
@ 0.45 MPa (66 psi), Unannealed			84	°C	184	°F	84	°C	
@ 1.8 MPa (264 psi), Unannealed			99	°C	210	°F	99	°C	
<b>Injection Molded Mechanical Properties</b>									
<b>Impact Strength:</b>									
Notched Izod (in) specimen @ 23°C (73°F)	12.7x3.2 mm (0.5x.125 in)	180/4A	D 256						
			21.4	J/m	0.4	ft-lb/in	2.2	kg-cm/cm	
Gardner Impact @ 23°C (73°F)		D 3029	0.113	J	1.0	in-lb	1.15	cm-kg	
<b>Tensile Properties</b> 12.7x3.2 mm (0.5x0.125 in) specimen:									
Yield Tensile Strength mm/min (0.2 in/min) rate	5	527	D 638	52	MPa	7500	psi	527	kg/cm <sup>2</sup>
Ultimate Tensile Strength mm/min (0.2 in/min) rate	5	527	D 638	52	MPa	7500	psi	527	kg/cm <sup>2</sup>
Ultimate Elongation mm/min (0.2 in/min) rate	5	527	D 638	2.1	%	2.1	%	2.1	%
Tensile Modulus mm/min (0.2 in/min) rate	5	527	D 638	2737	MPa	397,000	psi	27909	kg/cm <sup>2</sup>



<b>Flexural Properties</b>	1.3 mm/min (0.05 in/min) rate								
Flexural Strength (3-point)	178	D 790	108	MPa	15600	psi	1097	kg/cm <sup>2</sup>	
Flexural Modulus (3-point)	178	D 790	3103	MPa	450,000	psi	31635	kg/cm <sup>2</sup>	

- (1) When used unmodified for the manufacture of food contact articles, STYRON 695 will comply with Food Additive Regulations 21 CFR 177.1640 under the U.S. Food, Drug and Cosmetic Act. Such uses are subject to good manufacturing practices and any other limitations which are part of the statute or regulations. These should be consulted for complete details.
- (2) Typical properties, not to be considered as specification limits.
- (3) This numerical flame-spread rating is not intended to reflect hazards presented by material under actual fire conditions.

## Product Stewardship

Americas Styrenics has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with Americas Styrenics products – from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

## Customer Notice

Americas Styrenics strongly encourages its customers to review both their manufacturing processes and their applications of Americas Styrenics products from the standpoint of human health and environmental quality to ensure that Americas Styrenics products are not used in ways for which they are not intended or tested. Americas Styrenics personnel are available to answer your questions and to provide reasonable technical support. Americas Styrenics product literature, including safety data sheets, should be consulted prior to use of Americas Styrenics products. Current safety data sheets are available from Americas Styrenics.

## Medical Application Policy

Americas Styrenics will not knowingly sell or sample any product or service (“Product”) into any commercial or developmental application that is intended for:

- a. permanent (long term) contact with internal body fluids or internal body tissues. Long term is a use which exceeds 72 continuous hours
- b. use in cardiac prosthetic devices regardless of the length of time involved (Cardiac prosthetic devices include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass assisted devices);
- c. use as a critical component in medical devices that support or sustain human life; or
- d. use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.

Additionally, all Products intended for use in pharmaceutical applications, other than pharmaceutical packaging, must pass the current Pharmaceutical Liability Guidelines.

- For the products sold by the Americas Styrenics, new business opportunities require a business assessment prior to sale or sampling of Americas Styrenics products.
- Authorized distributors and resellers will adhere to this medical policy.
- Americas Styrenics does not endorse or claim suitability of their products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Americas Styrenics product is safe, lawful, and technically suitable for the intended use. AMERICAS STYRENICS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY AMERICAS STYRENICS PRODUCT FOR USE IN MEDICAL APPLICATIONS.

## Disclaimer

Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user’s specific application. Americas Styrenics, does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.

## Additional Information

**Headquarters**  
24 Waterway Avenue  
Suite 1200  
The Woodlands, TX 77380  
Toll Free 888-55-AMSTY (888-552-6789)

© AmericasStyrenics LLC 2008